



02054396

Andrews, David

From: GJRig01@oxy.com
Sent: Monday, June 07, 2010 6:05 AM
To: Andrews, David
Cc: Randy_Geddes@oxy.com; Brad_Ahlquist@Oxy.com; Ronald_Bevans@oxy.com; Simon_Benevides@oxy.com; Daniel_Padilla@oxy.com; Linda_Kuether@oxy.com
Subject: Well 697-17-08A, API# 05-045-17695-00 9-5/8" Surface Casing Cement Summary

Follow Up Flag: Follow up
Flag Status: Flagged

Mr. Andrews,

The following 9-5/8" surface casing string has been set at 2914' and cemented on Oxy's 609-14 pad:

Well 697-17-08A, API 05-045-17695-00

PRESSURE TESTED LINES TO 3000 PSI.
PUMPED 20 BBLS FRESH WATER, 20 BBLS OF SUPER FLUSH, 20 BBLS OF FRESH WATER.
CEMENTED 9-5/8" SURFACE CASING WITH:
1240 SACKS - 514 BBLS OF 12.3 PPG - 2.33 CU. FT/SK VERSACEM LEAD WITH TUFF FIBER, 160 SACKS - 59 BBLS OF 12.8 PPG - 2.07 CU. FT/SK VERSACEM TAIL. DISPLACED WITH 222 BBLS FRESH WATER AT 5-4-3 BPM.
SAW 550 PSI LIFT PRESSURE AT 2 BPM FOR THE LAST 15 BBLS.
BUMPED PLUG TO 500 PSI OVER LIFT PRESSURE.
INCREASED PSI TO 1500 PSI, AND TESTED CASING TO 1500 PSI FOR 30 MINUTES.
GOOD TEST. FLOATS HELD.
CIP AT 13:00, 06/06/2010.
SAW 0 BBLS CEMENT RETURNS TO SURFACE.

FLUSHED PARASITE LINE WITH 10 BBL SUGAR WATER.

TOPPED OUT OFFLINE AFTER SKIDDING TO WELL 697-17-08B. PUMPED TOTAL 210 SACKS - 67 BBLS OF 14 PPG - 1.78 CU. FT/SK HALCEM TOPOUT BLEND, UNTIL CEMENT RETURNED TO SURFACE WITHOUT FALLING BACK.

If you have any questions please contact OXY DSM

Thanks,

Simon Benavides, OB Sanchez, Dmitry Smushkov, Marco Silva

(281) 436-6424