



02054663

Andrews, David

From: GJRig02@oxy.com
Sent: Sunday, September 26, 2010 9:40 PM
To: Andrews, David
Cc: Brad_Ahlquist@Oxy.com; Simon_Benevides@oxy.com; Ronald_Bevans@oxy.com; OB_Sanchez@oxy.com; Dmitry_Smushkov@oxy.com; Victor_Guerra@oxy.com
Subject: CEMENT SURFACE 697-10-42C

Follow Up Flag: Follow up
Flag Status: Flagged

Mr. Andrews,

H&P 353 CEMENT SURFACE CASING DEPTH 2723' (API 0504519500) TESTED LINES TO 3000 PSI.
PUMPED 20 BBLS FRESH WATER, 20 BBLS OF SUPER FLUSH, 20 BBLS OF FRESH WATER.
CEMENTED 9.625" SURFACE CASING WITH:
1055 SACKS - 437 BBLS OF 12.3 PPG - 2.33 CU. FT/SK VERSACEM LEAD WITH TUFF FIBER, 160 SACKS
- 59 BBLS OF 12.8 PPG - 2.07 CU. FT/SK VERSACEM TAIL.
NO RETURNS THROUGHOUT CEMENT JOB.
DISPLACED WITH 206.3 BBLS FRESH WATER AT 6-4-2 BPM.
OBSERVED 535 PSI LIFT PRESSURE AT 2 BPM. BUMPED PLUG WITH 1000 PSI. FLOATS HELD FLUSHED
PARASITE LINE WITH 10 BBLS SUGAR H2O - HAD RETURNS AFTER 7.0 BBLS.
TOP JOB 497 SACKS, 12.5 PPG, 1.97 YIELD, HALCEM