

CEMENT JOB REPORT



Shoe Test (Update Original Treatment Report for Primary Job)

Depth Drilled out of Shoe:	0 FT	Target EMW: 0 LBS/GAL	Actual EMW: 0 LBS/GAL
Number of Times Tests Conducted:	0	Mud Weight When Test was Conducted:	0 LBS/GAL
Problems Before Job (I.E. Running Casing, Circulating Well, ETC)			
NA			
Problems During Job (I.E. Lost Returns, Equipment Failure, Bulk Delivery, Foaming, ETC)			
NA			
Problems After Job (I.E. Gas at Surface, Float Equipment Failed, ETC)			
NA			

PRESSURE/RATE DETAIL						EXPLANATION		
TIME HR:MIN.	PRESSURE - PSI PIPE	ANNULUS	RATE BPM	Bbl. FLUID PUMPED	FLUID TYPE	SAFETY MEETING: BJ CREW	CO. REP.	
						TEST LINES	4136 PSI	
						CIRCULATING WELL - RIG	X	BJ
11:30	0	0	0	0	NA	Pre rig up safety meeting		
13:00	0	0	0	0	NA	Pre job safety meeting		
13:38	4136	0	0	0	H2O	Pressure test		
13:42	1784	0	2	20	H2O	Fresh water spacer		
13:53	1743	0	2	20	H2O	Mud clean II		
14:03	1757	0	2	20	H2O	Freshwater spacer		
14:12	1608	0	1.9	130	CMT	Batch up and pump 250 sx. PLC + 4% Bentonite + 0.6% SM + 8 lbs/sack CSE-2 @ 11.0 ppg.		
14:38	1482	0	1.6	1.75	H2O	Displacement		
14:40	0	0	0	0	NA	Shut down for rig to pull pipe.		
16:14	804	0	1.6	41	CMT	Batch up and pump 360 sx. Type III Cement @ 14.5 ppg.		
17:10	0	0	0	0	NA	Rig down safety meeting		
BUMPED PLUG	PSI TO BUMP PLUG	TEST FLOAT EQUIP.	BBL.CMT RETURNS/ REVERSED	TOTAL BBL. PUMPED	PSI LEFT ON CSG	SPOT TOP OUT CEMENT	Service Supervisor Signature:	
Y <input type="checkbox"/> N <input checked="" type="checkbox"/>	0	Y <input type="checkbox"/> N <input checked="" type="checkbox"/>	21	232.75	0	Y <input type="checkbox"/> N <input checked="" type="checkbox"/>		