



02055125

Andrews, David

From: GJRig02@oxy.com
Sent: Tuesday, May 17, 2011 6:45 PM
To: Andrews, David
Cc: Simon_Benevides@oxy.com; Brad_Ahlquist@Oxy.com; Linda_Kuether@oxy.com;
Longworth, Mike; Daniel_Padilla@oxy.com; Nicolas_Carestia@oxy.com;
Joan_Proulx@oxy.com
Subject: OXY/H&P353/CC-697-08-08B/CC-608-41PAD 9.625" CEMENT SUMMARY

PUMPED 20 BBLS FRESH WATER, 20 BBLS OF FRESHWATER WITH GEL, 20 BBLS OF FRESH WATER.
CMT 9-5/8" 36LB. J-55 SURFACE CASING WITH:
1,050 SKS - 435.0 BBLS OF 12.3 PPG-2.33 CU. FT/SK VERSACEM LEAD, 170 SKS- 62.7 BBLS OF 12.8 PPG-2.07 CU.
FT/SK VERSACEM TAIL. 50% EXCESS DISPLACED WITH 205.6 BBLS FRESH WATER AT 6 BPM. OBSERVED 365
PSI LIFT PRESSURE AT 2 BPM.
BUMPED PLUG WITH 865 PSI. FLOATS HELD.
TEST 9-5/8" CASING TO 1,500 PSI FOR 30 MINUTES FLUSHED PARASITE LINE WITH 10BBLS SUGAR WATER
HAD RETURNS AFTER 6 BBLS. PRESSURE SPIKE AT 803 PSI.
TOP OUT JOB - 117 SKS - 41 BBLS CEMENT.
TOTAL CEMENT TO SURFACE 1 BBLS.

API# 05-045-18128-00 CASING SET AT 2703'

DEREK ADAM

OXY USA
H&P 353
DIRECT:281-436-6464