



**Andrews, David**

---

**From:** Matt Stark [mstark@foundationenergy.com]  
**Sent:** Saturday, August 25, 2012 8:42 AM  
**To:** Andrews, David  
**Subject:** Banta Ridge Federal 6-18 Surface Cement Job

Foundation Energy Management Subsequent Report  
Banta Ridge Federal 6-18-1-103  
05-103-11891

8/16/2012  
12 ¼" hole  
Set 8 5/8" 24# casing at 514'  
Pumped 250 sacks premium G cement, 1.15 yield, 15.8 #/gal  
Pumping at 100 psi  
Bumped plug at 150 psi, pressured up to 650 psi and held for 5 minutes  
No cement returns to surface  
Ran 1 inch into well  
Topped off with 100 sacks premium G cement, 1.15 yield, 15.8 #/gal  
5 bbls cement returns to surface