



# Job Summary

Ticket Number		Ticket Date	
TN#	FL1081	8/24/2016	

COUNTY	COMPANY	CUSTOMER REP
Jackson	Sandridge Energy	Chuck Marberry
WELL NAME	RIG	JOB TYPE
Evans 0780 7-21H	WMO 344	Surface
SURFACE WELL LOCATION		O-TEX Field Supervisor
Sec7 T7N R80W		Klosterman, Austin

EMPLOYEES		
	Peterson, Ryan	
	Davila, Israel	

### WELL PROFILE

Max Treating Pressure (psi):	2000	Bottom Hole Static Temperature (°F):	100
Bottom Hole Circulating Temperature (°F):	100	Well Type:	Oil

### Open Hole

1	Size (in)	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)
	12.25	0	2316	0	2309
2	Size (in)	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)

### Casing/Tubing/Drill Pipe

Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)
Surface	9.625	36	J-55	0	2316	0	2309
Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)
Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)

### CEMENT DATA

<b>Stage 1:</b>	From Depth (ft):	0	To Depth (ft):	1816.00
Type: Lead	Volume (sacks):	433	Volume (bbls)	166.5
Cement:	Control Set 'C'			Density (ppg)
Additives:	%2 CaCl2 + %2 SMS + %2 Gypsum + lb/sk0.25 Polyflake			Yield (ft^3/sk)
				Water Req.
				12.5    2.16    12.25

<b>Stage 2:</b>	From Depth (ft):	1,816	To Depth (ft):	2316.00
Type: Tail	Volume (sacks):	152	Volume (bbls)	45
Cement:	100% Class 'C'			Density (ppg)
Additives:	%1 CaCl2 + lb/sk0.25 Polyflake%			Yield (ft^3/sk)
				Water Req.
				13.5    1.67    8.83

<b>Stage 3:</b>	From Depth (ft):		To Depth (ft):	
Type: Top Off	Volume (sacks):		Volume (bbls)	
Cement:	100% Class 'C'			Density (ppg)
Additives:	%2 CaCl2			Yield (ft^3/sk)
				Water Req.
				13.5    1.67    8.83

### SUMMARY

Preflushes:	10 bbls of	Fresh Water	Calculated Displacement (bbl):	175.8
	bbls of		Actual Displacement (bbl)	175.8
	bbls of		Plug Bump (Y/N):	Yes
Total Preflush/Spacer Volume (bbl):	10		Bump Pressure (psi):	1700
Total Slurry Volume (bbl):	211.5		Lost Returns (Y/N):	N (if Y, when) Between 110 and 160 away
Total Fluid Pumped	397.3			
Returns to Surface:	Cement	30 bbls		

Thank You For Using

O - TEX Pumping

Customer Representative Signature: \_\_\_\_\_

