



**Bison Oil Well Cementing
Tail & Lead**

Date: 11/2/2016
 Invoice # 666027
 API# 05-123-43496
 Foreman: Nick Vigil

Customer: Noble Energy Inc.
 Well Name: Bennett LD19-765

County: Weld Consultant: Woody
 State: Colorado Rig Name & Number: H&P 517
 Distance To Location: 66 miles
 Units On Location: 3104/3215/3214
 Time Requested: 16:00
 Time Arrived On Location: 16:00
 Time Left Location: 20:30
 Sec: 19
 Twp: 9N
 Range: 58W

WELL DATA	Cement Data
Casing Size (in) : <u>9.625</u> Casing Weight (lb) : <u>40</u> Casing Depth (ft.) : <u>1,944</u> Total Depth (ft) : <u>1948</u> Open Hole Diameter (in) : <u>13.50</u> Conductor Length (ft) : <u>80</u> Conductor ID : <u>15.25</u> Shoe Joint Length (ft) : <u>51</u> Landing Joint (ft) : <u>36</u> Sacks of Tail Requested <u>100</u> HOC Tail (ft): <u>0</u> One or the other, cannot have quantity in both Max Rate: <u>8</u> Max Pressure: <u>2000</u>	Lead Cement Name: Cement Density (lb/gal) : <u>13.5</u> Cement Yield (cuft) : <u>1.7</u> Gallons Per Sack <u>9.00</u> % Excess <u>15%</u> Tail Cement Name: Cement Density (lb/gal) : <u>15.2</u> Cement Yield (cuft) : <u>1.27</u> Gallons Per Sack: <u>5.89</u> % Excess: <u>0%</u> Fluid Ahead (bbls) <u>50.0</u> H2O Wash Up (bbls) <u>20.0</u> Spacer Ahead Makeup Dye in second 10 bbl

Casing ID 8.835 Casing Grade J-55 only used

Lead Calculated Results	Tail Calculated Results
HOC of Lead <u>1612.57 ft</u>	Tail Cement Volume In Ann <u>127.00 cuft</u>
Casing Depth - HOC Tail	(HOC Tail) X (OH Ann)
Volume of Lead Cement <u>788.11 cuft</u>	Total Volume of Tail Cement <u>105.29 Cuft</u>
HOC of Lead X Open Hole Ann	(HOC Tail X OH Ann) - (Shoe Length X Shoe Joint Ann)
Volume of Conductor <u>61.05 cuft</u>	bbls of Tail Cement <u>22.62 bbls</u>
(Conductor ID Squared) - (Casing Size OD Squared) X (.005454) X (Conductor Length ft)	(HOC of Tail) X (OH Ann) + (Cement Yield) X (Shoe Joint Ann) X (.1781) X (% Excess)
Total Volume of Lead Cement <u>849.16 cuft</u>	HOC Tail <u>215.43 ft</u>
(cuft of Lead Cement) + (Cuft of Conductor)	(Tail Cement Volume) ÷ (OH Ann)
bbls of Lead Cement <u>173.92 bbls</u>	Sacks of Tail Cement <u>100.00 sk</u>
(Total cuft of Lead Cement) X (.1781) X (1+%Lead Excess)	(Total Volume of Tail Cement) ÷ (Cement Yield)
Sacks of Lead Cement <u>574.43 sk</u>	bbls of Tail Mix Water <u>14.02 bbls</u>
(Total Slurry Volume) ÷ (Cement Yield) X (% Excess Cement)	(Sacks of Tail Cement X Gallons Per Sack) ÷ 42
bbls of Lead Mix Water <u>123.09 bbls</u>	Pressure of cement in annulus
(Sacks Needed) X (Gallons Per Sack) ÷ 42	Hydrostatic Pressure <u>585.23 PSI</u>
Displacement <u>146.22 bbls</u>	Collapse PSI: <u>2570.00 psi</u>
(Casing ID Squared) X (.0009714) X (Casing Depth) + (Landing Joint) - (Shoe Length)	Burst PSI: <u>3950.00 psi</u>
Total Water Needed: <u>353.33 bbls</u>	

X WZ
 Authorization To Proceed

Customers hereby acknowledges and specifically agrees to the terms and condition on this work order, including, without limitation, the provisions on this work order.

