



5.5" Production

## Cement Post Job Report

Prepared For: Mr. Mike Schweizer  
Prepared Date: 12/26/2017  
Job Date: 12/22/2017

**PDC Energy, Inc.**

**Bunting 26P-212**

**Weld County, CO**

Prepared By: Adam DeSaules  
Phone: (432) 215-6693  
Email: [adam.desaules@otexpumping.com](mailto:adam.desaules@otexpumping.com)



# Job Summary

Ticket Number	Ticket Date
TN# FL2807	12/22/2017

COUNTY	COMPANY	API Number
Weld	PDC Energy, Inc.	05-123-44088
WELL NAME	RIG	JOB TYPE
Bunting 26P-212	Ensign 161	Production
SURFACE WELL LOCATION	O-TEX Field Supervisor	CUSTOMER REP
SWSE 26-5N-65W	Kopp, Jeff	Brady Sharp

EMPLOYEES		
Collin, Justin	Brophy, Mike	
Peterson, Ryan		
St. John, Gary		

<b>WELL PROFILE</b>			
Max Treating Pressure (psi):	2500	Bottom Hole Static Temperature (°F):	210
Bottom Hole Circulating Temperature (°F):		Well Type:	Oil

Open Hole						
1	Size (in)	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)	
	8.5	15155	1632			
2	Size (in)	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)	

Casing/Tubing/Drill Pipe							
Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)
Surface	9.625	36	J-55	1632	0		
Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)
Production	5.5	20	P-110	15155	0		
Type	Size (in)	Weight (lb/ft)	Grade	TMD From (ft)	TMD to (ft)	TVD From (Ft)	TVD to (Ft)

<b>CEMENT DATA</b>							
Stage 1:	From Depth (ft):	15155	To Depth (ft):	2500			
Type: SingleSlurry	Volume (sacks):	1665	Volume (bbls):	534			
Cement & Additives:							
100% 35:65:0(POZ:G:GEL)+0.4% ASM-3+0.3% CFR+0.6% C-17+25% Silica Flour				Density (ppg):	13.5	Yield (ft <sup>3</sup> /sk):	1.80
				Water Req.:		8.77	

<b>SUMMARY</b>							
Preflushes:	40 bbls of	SAPP	Calculated Displacement (bbl):	Stage 1	336	Stage 2	
	50 bbls of	Weighted Spacer	Actual Displacement (bbl):		335		
	10 bbls of	Fresh Water	Plug Bump (Y/N):	Y	Bump Pressure (psi):	2648	
Total Preflush/Spacer Volume (bbl):	100		Lost Returns (Y/N):	N	(if Y, when)		
Total Slurry Volume (bbl):	534						
Total Fluid Pumped	969						
Returns to Surface:	Cement	0 bbls					
Job Notes (fluids pumped / procedures / tools / etc.):	Job pumped per customers request. Job went well						

Customer Representative Signature: \_\_\_\_\_

**Thank You For Using  
O-TEX Cementing**

