



# Bison Oil Well Cementing Single Cement Surface Pipe

Date: 5/29/2018  
 Invoice # 200296  
 API# \_\_\_\_\_  
 Foreman: Kirk Kallhoff

**Customer:** Anadarko Petroleum Corporation

**Well Name:** gracie 24-8hz

County: Weld  
 State: Colorado  
 Sec: 24  
 Twp: 2n  
 Range: 66w

Consultant: bryan  
 Rig Name & Number: CARTEL 88  
 Distance To Location: 30  
 Units On Location: 1  
 Time Requested: 800 pm  
 Time Arrived On Location: 600 pm  
 Time Left Location: 11:00pm

WELL DATA		Cement Data	
Casing Size OD (in) :	<u>9.625</u>	Cement Name:	<u>BFN III</u>
Casing Weight (lb) :	<u>36.00</u>	Cement Density (lb/gal) :	<u>14.2</u>
Casing Depth (ft.) :	<u>1,866</u>	Cement Yield (cuft) :	<u>1.48</u>
Total Depth (ft) :	<u>1876</u>	Gallons Per Sack:	<u>7.48</u>
Open Hole Diameter (in.) :	<u>13.50</u>	% Excess:	<u>10%</u>
Conductor Length (ft) :	<u>80</u>	Displacement Fluid lb/gal:	<u>8.3</u>
Conductor ID :	<u>15.5</u>	BBL to Pit:	
Shoe Joint Length (ft) :	<u>40</u>	Fluid Ahead (bbls):	<u>30.0</u>
Landing Joint (ft) :	<u>8</u>	H2O Wash Up (bbls):	<u>10.0</u>
Max Rate:	<u>8</u>	<b>Spacer Ahead Makeup</b>	
Max Pressure:	<u>2000</u>	<b>30 BBL WATER, DYE IN 2ND 10</b>	

Calculated Results	Displacement:	141.78 bbls
<b>cuft of Shoe</b> <u>17.36</u> <b>cuft</b> (Casing ID Squared) X (.005454) X (Shoe Joint ft)	(Casing ID Squared) X (.0009714) X (Casing Depth + Landing Joint - Shoe Joint)	
<b>cuft of Conductor</b> <u>64.40</u> <b>cuft</b> (Conductor Width Squared) -(Casing Size OD Squared) X (.005454) X (Conductor Length ft)	<b>Pressure of cement in annulus</b>	
<b>cuft of Casing</b> <u>960.16</u> <b>cuft</b> (Open Hole Squared)-(Casing Size Squared) X (.005454) X (Casing Depth - Conductor Length )	<b>Hydrostatic Pressure:</b> <u>1376.55 PSI</u>	
<b>Total Slurry Volume</b> <u>1041.93</u> <b>cuft</b> (cuft of Shoe) + (cuft of Conductor) + (cuft of Casing)	<b>Pressure of the fluids inside casing</b>	
<b>bbls of Slurry</b> <u>185.57</u> <b>bbls</b> (Total Slurry Volume) X (.1781)	<b>Displacement:</b> <u>787.34 psi</u>	
<b>Sacks Needed</b> <u>704</u> <b>sk</b> (Total Slurry Volume) ÷ (Cement Yield) X (% Excess Cement)	<b>Shoe Joint:</b> <u>29.51 psi</u>	
<b>Mix Water</b> <u>125.38</u> <b>bbls</b> (Sacks Needed) X (Gallons Per Sack) ÷ 42	<b>Total</b> <u>816.84 psi</u>	
	<b>Differential Pressure:</b> <u>559.70 psi</u>	
	<b>Collapse PSI:</b> <u>2020.00 psi</u>	
	<b>Burst PSI:</b> <u>3520.00 psi</u>	
	<b>Total Water Needed:</b> <u>307.16 bbls</u>	

X \_\_\_\_\_  
 Authorization To Proceed



# SERIES 2000

