

FREMONT PAVING and REDI-MIX, INC.



839 Mackenzie Avenue
P. O. Box 841
Cañon City, Colorado 81215

Telephone:
(Bus.) 719 - 275-3264
(Fax) 719 - 275-8897



INIT WEIGHT	SLUMP TEST	AIR TEST	TEMP	CYLINDERS	TIME	LEAVE PLANT
CUSTOMER ID	P.O. NO./PROJECT NO.	TRUCK	DATE	DRIVER	14:00	ARRIVE JOB
1268		F309	6/28/18	ZAK		2:30
SOLD TO			JOB LOCATION			FINISH POURING
JAVERNICK DILL			315 LONGS PEAK			LEAVE JOB
						ARRIVE PLANT

QUANTITY THIS LOAD	QUANTITY ORDERED	QUANTITY DELIVERED	PRODUCT DESCRIPTION	UNIT OF MEASURE	UNIT PRICE	EXTENDED PRICE
10.00 yd			WELL MIX - 2 10 SACK GROUT		\$218.00	\$2,180.00

INSTRUCTIONS						
SLUMP: 4-6"						
DELIVERY INSTRUCTIONS:						
					SUB TOTAL	\$2,180.00
					TAX	
					TOTAL	\$2,297.72

GENERAL TERMS AND CONDITIONS OF DELIVERY

The purchaser agrees to provide suitable roadways or approaches to points of delivery when material is to be delivered by trucks in places other than paved streets. We reserve the right to stop deliveries if the roadways or approaches are unsatisfactory to us. In the event purchaser orders delivery beyond curb line, we will not assume liability for damage to sidewalks, driveways or other property and Purchaser hereby agrees to indemnify and hold Fremont Paving & Redi-Mix harmless against all liability, loss and expense incurred as a result of such deliveries. Customer is responsible for wrecker fees required on this delivery.

We agree to pay an annual percentage rate of 24%. Failure to pay when agreed is basis for legal action to be taken and buyer agrees in event of suit to pay all cost of collection and reasonable attorney fees and hereby waives all rights of exemption as to personal property under the laws of the state of Colorado or any other state.

Customer is required to provide mixer truck wash out on site.

Fremont Paving & Redi Mix, Inc. agents and/or drivers may refuse to allow foreign chemicals to be added to the "mixer" at any time. Customer assumes full responsibility for the mix if he/she adds any water or other materials to the mix.

We allow one hour unloading time free; any additional time will be billed at our normal rate.

C.O.D. Deliveries must be paid on delivery.

WE DO NOT GUARANTEE FINISHED RESULTS obtained from this load of concrete, as many important factors affecting the ultimate quality of the completed job are out of our control. We will not be responsible for any shortages if they are not reported at the time of delivery.

Water added on job 25

ADDED INGREDIENTS: Purchaser assumes FULL RESPONSIBILITY for strength, slump and quality of concrete when additional water or other material is requested on the job site. This load of concrete is produced in accordance with standard Specifications for Ready Mixed Concrete, A.S.T.M. Designation C-94-81 and the quality is guaranteed to be as indicated on the ticket with tested in accordance with these specifications. WARNING: Freshly mixed cement, mortar, concrete or grout contains chemicals which may cause skin irritation. Avoid contact with skin; take these PRECAUTIONS & KEEP AWAY FROM CHILDREN; Avoid all contact with eyes. Wear rubber boots and gloves and avoid prolonged contact directly with skin. In case of contact with skin or eyes: FLUSH THOROUGHLY WITH WATER. If irritation persists, promptly seek medical attention.

CUSTOMER'S REPRESENTATIVE

35490

PLEASE PAY FROM THIS INVOICE

Truck	Driver	User	Disp Ticket	Num	Ticket ID	Time	Date
F309	ZAK	user			8822	14:00	6/28/18
Load Size	Mix Code	Returned	Qty	Mix Age	Seq	Load ID	
10.00 yd	WELL MIX 2				D1	8996	

Material	Design Qty	Required	Batched	% Var	% Moisture	Actual	Wat
SAND	2370 lb	23707 lb	23620 lb	-0.37%	0.03% E		1 gl
CEM1-2	735 lb	7350 lb	7350 lb	0.00%			
F-ASH	188 lb	1880 lb	1865 lb	-0.80%			
WATER	50.0 gl	499.1 gl	500.0 gl	0.17%		500.0 gl	

Actual		Num Batches	1				14:07:33				
Load	37002 lb	Design W/C	0.451	Water Cement	0.453 A	Design	500.0 gl	Actual	500.9 gl	To Add	0.0 gl
Slump	4.00 in	Water in Truck	0.0 gl	Adjust Water		0.0 gl / Load	Trim Water	0.0 gl /	yd	Note: Manual feed occurred	
Actual W/C Ratio	0.453	Actual Water	501 gl	Batched Cement		9215 lb	Allowable Water	0 lb	0.0		

FREMONT PAVING and REDI-MIX, INC.



839 MacKenzie Avenue
P. O. Box 841
Cañon City, Colorado 81215

Telephone:
(Bus.) 719 - 275-3264
(Fax) 719 - 275-8897



UNIT WEIGHT	SLUMP TEST	AIR TEST	TEMP	CYLINDERS	TIME	LEAVE PLANT
CUSTOMER ID	PO. NO./PROJECT NO.	TRUCK	DATE	DRIVER	17:10	ARRIVE JOB
SOLD TO	JOB LOCATION					FINISH POURING
JAVERNICK OIL		315 LONGS PEAK				LEAVE JOB
						ARRIVE PLANT

QUANTITY THIS LOAD	QUANTITY ORDERED	QUANTITY DELIVERED	PRODUCT DESCRIPTION	UNIT OF MEASURE
5.00 5.00 yd	5.00	5.00	WELL MIX 2 10 SACK GROUT	

INSTRUCTIONS

SLUMP 4.00

DELIVERY INSTRUCTIONS:

GENERAL TERMS AND CONDITIONS OF DELIVERY

- The purchaser agrees to provide suitable roadways or approaches to points of delivery when material is to be delivered by trucks in places other than paved streets. We reserve the right to stop deliveries if the roadways or approaches are unsatisfactory to us. In the event Purchaser orders delivery beyond curb line, we will not assume liability for damage to sidewalks, driveways or other property and Purchaser hereby agrees to indemnify and hold Fremont Paving & Redi-Mix harmless against all liability, loss and expense incurred as a result of such deliveries. Customer is responsible for wrecker fees required on this delivery.
- We agree to pay an annual percentage rate of 24%. Failure to pay when agreed is basis for legal action to be taken and buyer agrees in event of suit to pay all cost of collection and reasonable attorney fees and hereby waives all rights of exemption as to personal property under the laws of the state of Colorado or any other state.
- Customer is required to provide mixer truck wash out on site.
- Fremont Paving & Redi Mix, Inc. agents and/or drivers may refuse to allow foreign chemicals to be added to the "mixer" at any time. Customer assumes full responsibility for the mix if he/she adds any water or other materials to the mix.
- We allow one hour unloading time free; any additional time will be billed at our normal rate.
- C.O.D. Deliveries must be paid on delivery.
- WE DO NOT GUARANTEE FINISHED RESULTS obtained from this load of concrete, as many important factors affecting the ultimate quality of the completed job are out of our control. We will not be responsible for any shortages if they are not reported at the time of delivery.

Water added on job _____

ADDED INGREDIENTS: Purchaser assumes FULL RESPONSIBILITY for strength, slump and quality of concrete when additional water or other material is requested on the job site. This load of concrete is produced in accordance with standard Specifications for Ready Mixed Concrete, A.S.T.M. Designation C-94-81 and the quality is guaranteed to be as indicated on the ticket with tested in accordance with these specifications. **WARNING:** Freshly mixed cement, mortar, concrete or grout contains chemicals which may cause skin irritation. Avoid contact with skin; take these **PRECAUTIONS & KEEP AWAY FROM CHILDREN:** Avoid all contact with eyes. Wear rubber boots and gloves and avoid prolonged contact directly with skin. In case of contact with skin or eyes. **FLUSH THOROUGHLY WITH WATER.** If irritation persists, promptly seek medical attention.

J. [Signature]
CUSTOMER'S REPRESENTATIVE

35501 CC

PLEASE PAY FROM THIS INVOICE

Truck	Driver	User	Disp Ticket	Num	Ticket ID	Time	Date
F309	ZAK	user			8824	15:18	6/28/18
Load Size	Mix Code	Returned	Qty	Mix Age	Seq	Load ID	
5.00 yd	WELL MIX 2				D1	8998	

Material	Design Qty	Required	Batched	% Var	% Moisture	Actual	Wat
SAND	2370 lb	11854 lb	11800 lb	-0.45%	0.03% E		gl
CEM1-2	735 lb	3675 lb	3665 lb	-0.27%			
F-ASH	188 lb	940 lb	945 lb	0.53%			
WATER	500 gl	249.6 gl	250.0 gl	0.17%		250.0 gl	

Actual		Num Batches:	1									
Load	18493 lb	Design W/C:	0.451	Water/Cement:	0.453	A	Design	250.0 gl	Actual	250.4 gl	To Add	0.0 gl
Slump:	4.00 in	Water in Truck:	0.0 gl	Adjust Water:	0.0 gl / Load	Trim Water:	0.0 gl /	yd				
Actual W/C Ratio:	0.453	Actual Water:	250 gl	Batched Cement:	4610 lb	Allowable Water:	0 lb	0.0				