



**Occidental Petroleum Corporation**

**BERRY FARMS 8-5HZ**

**API # 512351862**

**Surface Casing**

**Date: November 18, 2022**





## 2. Cement Blend Data

This is the blend data of the Cement ordered for the job.

Blend Description	Cement Properties
Base Cement Blend : MAG S 14.1	
Mix Water (gal/sk)	5.89
Yield (ft <sup>3</sup> /sk)	1.28
Lab Results	
Density (ppg)	14.1
Working Time (hr:min)	2:13
Thickening Time (hr:min)	3:05
Compressive Strength (psi/12h)	698
Compressive Strength (psi/24h)	1070
Mix water Temperature (°F)	68
Slurry Temperature (°F)	68





## BERRY FARMS 8-5HZ – Surface Casing

### 4. Job Graph

