

# Southplus Inc.

---

## 15P/20P-TPU Liner TDS

Items	Value/Unit		Test method
Base fabric	Polyester		
Coating type	TPU		
Yarn	1000×1000 D		Panama weaving
Construction	16 x 16 /sq. cm	40 x 40/sq. inch	
Total Weight	1250 g/sq. m	36.9 oz/sq. yard	
Thickness	1.13 mm		
Breaking Strength, Strip (Warp/Weft)	5583/5072 N/5 cm	627/570 Lb./inch	ASTM D751
Tear strength, Single tongue (Warp/Weft)	215/168 N	48/38 Lb.	ASTM D751
Adhesion (IVK)	250 N/5 cm	28 Lb./inch	ASTM D751
Temperature resistance	-54~+93 °C	-65~+200 °F	ASTM D2136/D1204

### Technical Statement

Customers should choose our product properly according to the related stipulation and standard. We take responsibility for technical data on this page and won't undertake any other legal duties other than this.

(The technical data of this page is all arithmetical average and the tolerance permitted is 5 percent above or under)