



CEMENT | FLUID | INFRASTRUCTURE SERVICES

WWW.MAGNUMSERVICES.COM



## Post Job Report

Prepared for CIVITAS RESOURCES

Grimm Motocross 4-65 23- 1B2BUH

API #05-005-07574

Surface Casing Cement

July 06 2025

#### Disclaimer and Confidentiality Statement

This report and all accompanying materials, are confidential and intended solely for the use of the individual or entity to whom they are addressed. The interpretations provided by the Magnum Cementing Services Technical Team are based on available data and best practices at the time of reporting. If you are not the intended recipient, you are hereby notified that any disclosure, copying, distribution, or use of this information is strictly prohibited. If you have received this report in error, please notify the sender immediately and delete it from your system. Magnum Cementing Services assumes no responsibility for decisions made based on the contents of this report. The final use and application of the information contained herein remain the sole responsibility of the Customer.



## US Treatment Report

<b>Customer:</b> CIVITAS RESOURCES		<b>Job #:</b> JOB00213800	
<b>Rep:</b> Danny Herrera	<b>Rig:</b> Patterson 345	<b>Job Date:</b> Jul 06 @ 00:00	
<b>Supervisor:</b> ANTHONY GARCIA	<b>Well:</b> Grimm Motocross 4-65 23 1B2BUH	<b>Time Requested:</b> Jul 06 @ 00:00	
<b>Job Type:</b> US Primary	<b>UWI:</b> Grimm Motocross 4-65 23 1B2BUH	<b>Time Arrived:</b> Jul 09 @ 01:30	
Casing-Surface	<b>Surface:</b> Grimm Motocross 4-65 23 1B2BUH	<b>Time Released:</b> Jul 09 @ 14:00	

1604.9 sk MAG S 13.3 + 0.10% MCDF-P + 1.00% MCLC-2 + 0.10% MCLC-F

Yield: 1.46 ft<sup>3</sup>/sk = 417.32bbls    Mix Water: 7.05 gal/sk = 269.39 bbl

BHST (F)	151	Surface Casing Size (in)	9.625	Surface Casing Grade	J-55
Surface Casing Weight (lb/ft)	36	Casing Size (in)	15.562	Collapse Csg Pressure (psi)	2020
Float Depth (ft)	3928	Funnel Vis (sec/qt)	TBD	Max Csg Pressure (psi)	3520
Max Pressure (psi)	1500	Mud Density (lb/gal)	8.4	Mud Type	FW
Plug Size (in)	9.625	Plug Type	Rig	TMD (ft)	3974
TVD (ft)	3566		Supplie d		

Treatment Info:    Sacks Used: 1604.9    Sacks Not Used: 0

Preflush: 5bbls Fresh Water & 10bbls MAG Mark & 10bbls Fresh Water	Circulation Time: 1
Displace:	Slurry Temp: 78    Bulk Sample: Yes
	Water Temp: 72    Water Sample: Yes
	Bulk Temp: 90    Slurry Sample: Yes
	Air Temp: 96    Air Pressure 29.7
Slurry Returns: 10 Plug Bumped: Yes Pump Out Lines: No    Float Held: Yes	
Cement Class: Type III    Humidity: 8    Precipitation: 0	

**Further Blend Details:**

Prehydrated:

Additional Details (General Notes):    CASING SET DEPTH AT 3,964'

Time	Pressure psi	Annular Pressure psi	Volume Per Stage bbls	Total Stage Volume bbls	Rate bbls/mi n	Treatment Detail
00:00	0.00					Arrive on Location - GET NUMBERS FROM COMPANY TEST WATER TEMP-72 PH-6 CLHORIDES-100 HARDNESS-120
08:30	0.00					Safety Meeting - GO OVER JOB PROCEDURE AND SAFETY WITH RIG CREW AND MAGNUM CREW
10:38	100.00			5	4	Fill Lines - LOADED BOTTOM PLUG INTO CASING VERIFIED BY COMPANY MAN
10:40	2,500.00			0.5	.5	Start Pressure Test - TEST LINES 2500 PSI
10:44	100.00			20	4	Pump Preflush - 10 BBLS MAG MARK 10 BBLS FRESH WATER

10:51	400.00			417	7.5	Pump Slurry - 1604.9 SKS/ 417 BBLS OF MAG S 13.3 PPG YIELD 1.46 GAL./SK 7.05 VERIFIED WITH PRESSURIZED SCALES
11:52	0.00					Stop Pumping
11:53	0.00					Drop Plug - WITNESSED BY COMPANY MAN
11:54	800.00			280	8.5	Displace
12:32	1,000.00			23.7	4	Decrease Rate - SLOWED RATE TO BUMP PLUG
12:36	1,500.00					Bump Plug - TOTAL DISPLACEMENT 303.7 BBLS 10 BBLS OF CEMENT TO SURFACE
12:39	1,540.00					Start Pressure Test - 30 MINUTE CASING TEST
13:10	0.00					Check Floats - 1 BBL BACK
13:15	0.00					Wash Up Truck
14:00	0.00					Leave Location

--



Customer: CIVITAS

Date: July 9, 2025

Ticket: 213800

Location: Grimm Motocross 4-65 23 1B2BUH

Well Name: Grimm Motocross 4-65 23 1B2BUH

Job Type: SURFACE

Magnum Unit #: 1507

